

Pro-Seal Aqua Flex™



Polycarbon/Polycarbonate Liquid Applied Elastomeric Coating

Product Description

Pro-Seal Aqua Flex™ is a polycarbon/polycarbonate single component elastomeric coating with exceptional elongation and elasticity.

Advantages

- Easy to install
- Use on substrates that require expansion & contraction over broad temperature ranges (-20°F to 180°F)
- Easy to repair
- May bridge minor surface imperfections
- Custom colors available

Applications

- Concrete
- CMU Block
- Stucco
- Areas of greater expansion and contraction requiring a water barrier

Instructions

1. Surface must be dry, clean and free of all loose particulate and bond-breaking matter.
2. For specific application instructions or guide specifications, contact us at 800.349.7325 or information@prosealproducts.com

Technical Support

For technical support: 800.349.7325 or information@prosealproducts.com

Technical

Information	Value
Material	1 part
Appearance	Liquid
Application	See guide specification
Application temp.	> 53°F
Application humidity	< 80%
Stain resistance	Good
Dry film	6-8 mils
Density	8.2-8.5 lbs/gal
Color	White
Spread rate: 10 mils 7 mils	100 sq. Ft. / gal 150 sq. Ft. / gal
Solids	62.5% wt x 49% vol
Tack free cure time	2-4 hours
Dry cure time	8 hours
Shelf life	24 months when stored properly
Storage indoors	60°F-110°F
Packaging:	1 gallon, 5 gallons and 55 gallons

Cautions

Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.



Pro-Seal Aqua Flex™



Polycarbon/Polycarbonate Liquid Applied Elastomeric Coating

Specifications

Test	Data	Value
ASTM D 2370	Tensile strength @ 75°F	655 psi
ASTM D 2730	Elongation @ 75°F	350%
ASTM D 1653	Water vapor permeance @ 75°F	9 perm
ASTM D 822	Weathero-meter	No deterioration or chalking after 2,000 cycles
Brookfield viscometer	Viscosity	110-116 ku
ASTM D 2369-2398	V.O.C. content	50 g/l

* Data based on laboratory tested materials.

Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.



16541 Redmond Way • Suite 363C • Redmond, WA 98052
Phone: 800.349.73256 • information@prosealproducts.com
www.prosealproducts.com • © Copyright Pro-Seal