

# Pro-Seal DP-36<sup>®</sup>



## Fluid Contaminant Extractant & Deep Penetrating Sealer

### Product Description

**Pro-Seal DP-36<sup>®</sup>** is a single component polycarbon/polycarbonate reactive osmotic reagent that seals, densifies, hardens, reduces vapor drive and preserves most concrete substrates when used as part of a Pro-Seal<sup>®</sup> system.

### Advantages

- NSF 61 Certified
- No V.O.C.
- Leaves a clear natural finish with no film or membrane on the surface
- Provides a prepared surface for better bonding of concrete toppings, coatings, mastics, and paints
- Extracts fluid contaminants from the in situ structures of concrete
- Forms a hydrostatic barrier in concrete that greatly reduces vapor drive
- Gives concrete some waterproof characteristics.

### Applications

- On Grade
- Below Grade
- Negative Side
- Vertical or Horizontal applications

\*Intended for use on concrete only. Not intended for pigmented surfaces. Keep away from glass. Always apply a test patch before application. Pro-Seal DP-36<sup>®</sup> will not bridge cracks, voids or gaps. Use only on intended surfaces, protection of property required.

### Technical Support

For technical support: 800.349.7325 or [information@prosealproducts.com](mailto:information@prosealproducts.com)

### Instructions

1. Surface must be clean and free of all loose particulate and bond-breaking matter.
2. Wet area with de-ionized water, leaving no standing water.
3. Apply at an average coverage rate of between 600 and 800 square feet per gallon using a low-pressure sprayer.
4. Wait for 48 hours, and then apply the Pro-Seal<sup>®</sup> specified system.
5. For specific application instructions or guide specifications, contact Pro-Seal's Technical Department at 800.349.7325 or [information@prosealproduct.com](mailto:information@prosealproduct.com)

### Technical

Information	Value
Material	1 Part
Mix Time	N/A
Appearance	Liquid
Application	See Guide Specification
Cure Time	48 Hrs Walk able
Full Cure	14 Days
Freezing Temp	32° F
Boiling Point	212° F
Flammability	None
Environmental Hazards	None
Shelf Life	2 Years When Stored Properly
Packaging	1 Gallon, 5 Gallons and 55 Gallons

Pro-Seal DP-36<sup>®</sup>



16541 Redmond Way • Suite 363C • Redmond, WA 98052  
Phone: 800.349.7325 • [information@prosealproducts.com](mailto:information@prosealproducts.com)  
[www.prosealproducts.com](http://www.prosealproducts.com) • © Copyright Pro-Seal

# Pro-Seal DP-36®



## Fluid Contaminant Extractant & Deep Penetrating Sealer

### Specifications

Concrete Specimens Tested as Follows		
Test	Data	Value
ASTM C 67 Section 7	Decreased Absorption	25%
ASTM C 67 Section 14	Decreased Suction	35%
ASTM C 67 Section 10	Efflore-Scence	None
ASTM C 67 Section 6	Compressive Strength	@ 8 Days +15%
ASTM C 67 Section 6	Compressive Strength	@ 31 Days +23%
ASTM C 156	Concrete Curing Against Hairline Cracking & Spot Drying	Significant Improve-Ment
ASTM C 666	Freeze-Thaw Damage	75% Improved Resistance
ASTM C 666 Using 5% Nacl	Salt Attack In Presence Of Moisture	60% Improved Resistance
Orf Method	Dusting Due To Abrasion	100% Improved Resistance

\* Data based on laboratory tested materials.

### Cautions

Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

### Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

Pro-Seal DP-36®



16541 Redmond Way • Suite 363C • Redmond, WA 98052  
Phone: 800.349.7325 • [information@prosealproducts.com](mailto:information@prosealproducts.com)  
[www.prosealproducts.com](http://www.prosealproducts.com) • © Copyright Pro-Seal