



# Pro-Seal Hydro Paint II™

## Polycarbon/Polycarbonate Light Coating

### Product Description

Pro-Seal Hydro Paint II™ is a polycarbon/polycarbonate two component coating with **non-solvent** extender.

### Advantages

- Easy to install
- High density
- 100% solid
- May be applied in damp environments when used with Pro-Seal DP-36®
- Has a wide range of good chemical resistance
- Unlike epoxies and urethanes as it is easily spot-repairable

### Applications on concrete

- Damp environments
- Production areas where high-volume traffic causes wear and tear on surface
- Mild secondary containment

### Instructions

1. Surface must be dry, clean and free of all loose particulate and bond-breaking matter.
2. For specific application instructions or guide specifications, contact Pro-Seal's Technical Department at 800.349.7325 or [information@prosealproducts.com](mailto:information@prosealproducts.com)

### Technical

Information	Value
Material	2 Part
Mix Time	4 Minutes
Appearance	Liquid
Application	See Guide Specification
Flash Point	500°F
Application Per Coat	1-14 Mils
Stain Resistance	Excellent
Pot Life	45 Minutes
Cure To Walkable	6 Hours
Full Cure	96 Hours
Shelf Life	Up To 12 Months When Stored Properly
Packaging:	2 Part Kits

### Technical Support

Contact our technical dept. at 800.349.7325 or [information@prosealproducts.com](mailto:information@prosealproducts.com)

### Cautions

Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.



# Pro-Seal Hydro Paint II™



## Polycarbon/Polycarbonate Light Coating

### Specifications

Test	Data	Value
ASTM D 695	Compressive strength	1,000 psi
ASTM D 1706	Cured hardness	85 Shore D
ASTM D 638	Tensile strength	900 psi
ASTM D 2566	Cure shrinkage	.003 inches
ASTM D 790	Flexural strength	900 psi
ASTM D 1002	Adhesive tensile shear	400 psi
Taber abrasion resistance	1,000 gm head cs 17 wheel wt loss 1,000 cycles	.00 mg
Taber abrasion resistance	1,000 gm head cs 17 wheel wt loss 350,000 cycles	.005 mg

\* Data based on laboratory tested materials.

### Chemical Resistance

Cured material	Rating
Hydrochloric acid	Excellent
Sulfuric acid 60%	Fair
Nitric acid 25%	Fair
Chromic acid	Very good
Kerosene	Excellent
Methanol	Very good
Toluene	Very good
Ammonia	Excellent
Nitrates	Poor
Chlorinated solvent	Very good
Phenol	Poor
Sodium hydroxide 10%	Excellent

### Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

