

Pro-Seal Power Kote II™



Polycarbon/Polycarbonate Two Part Coating

Product Description

Pro-Seal Power Kote II™ is a polycarbon/polycarbonate high density two-part chemical and wear resistant coating. This product is designed to approach an entire infrastructure repair or new construction challenge.

Advantages

- Easy to install
- Performs best in harsh chemical environments
- Impervious to U.V. attack
- Easily spot repairable

Applications

- Primary Containment
- Secondary Containment
- Structural Preservation
- Rehabilitation
- Cosmetic improvement to high traffic, and chemically exposed areas

Instructions

1. Surface must be dry, clean and free of all loose particulate and bond-breaking matter.
2. For specific application instructions or guide specifications, contact Pro-Seal's Technical Department at 425.488.6570 or information@prosealproducts.com

Technical

Information	Value
Material	2 part
Mix time	4 minutes
Appearance	Paste
Application	See guide specification
Flash point	500°F
Pot life	45 minutes
Stain resistance	Excellent
Application per coat	1-120 mils
Cure to walkable	6-12 hours
Full cure	96 hours
Packaging:	2 part kit

Technical Support

Contact our technical dept. at 425.488.6570 or information@prosealproducts.com

Cautions

Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

Pro-Seal Power Kote II™



Pro-Seal Power Kote II™



Polycarbon/Polycarbonate Two Part Coating

Specifications

Test	Data	Value
ASTM D 695	Compressive strength	23,000 psi
ASTM D 1706	Cured hardness	88 shore D
ASTM D 790	Flexural strength	6,160 psi
ASTM D 1002	Adhesive tensile sheer	2,600 psi
ASTM D 638	Tensile strength	3,200 psi
ASTM D 2586	Cure shrinkage	.002 in
Taber abrasion resistance	500 gm head cs 17 wheel wt loss 1,000 cycles 350,000 cycles	0 MG .001 MG
FST 141 A method 4044	Total solids	100%
FST 141 A method 4291	Viscosity mixed 2 parts	7,000 cps

* Data based on laboratory tested materials.

Chemical Resistance

Cured material	Rating
Hydrochloric acid	Excellent
Sulfuric acid 60%	Very good
Nitric acid 25%	Very good
Chromic acid	Excellent
Kerosene	Excellent
Methanol	Excellent
Toluene	Excellent
Ammonia	Excellent
Nitrates	Excellent
Chlorinated solvent	Excellent
Phenol	Excellent
Sodium hydroxide 10%	Excellent
Sulfates	Very good

Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

Pro-Seal Power Kote II™



16541 Redmond Way • Suite 363C • Redmond, WA 98052
Phone: 425.488.6570 • Fax: 425.488.6926 • information@prosealproducts.com
www.prosealproducts.com • © Copyright Pro-Seal