

Pro-Seal R.O.C. Hard™



Non-Solvent Surface Hardening & Polishing Agent

Product Description

Pro-Seal R.O.C. Hard™ is a single component polycarbon/polycarbonate concrete hardening agent. This product cures and polishes concrete to a high-shine “Rock Hard” finish.

Advantages

- Non-solvent
- Increases hardness up to 21%
- No V.O.C.
- Meets or exceeds USDA standards for food areas
- Moisture resistant

Applications on Concrete

- Retail Floors
- Warehouse Floors
- Commercial Kitchen Floors
- Schools
- And more!

Application

1. Surface must be clean and free of all loose particulate and bond-breaking matter.
2. For specific application instructions or guide specifications, contact us at 800.349.7325 or information@prosealproducts.com

Technical Support

Contact our technical dept. at 800.349.7325 or information@prosealproducts.com

Technical

Information	Value
Material	1 part
Mix time	None
Appearance	Liquid
Application	See guide specification
V.O.C. content	N/A
Flash point	230°F
Cure time to touch	.75 hours
Cure time complete	2 hours
Stain resistance	N/a
Penetrates	1-22 mils
Specific gravity	8.46
Packaging:	1 gallon, 5 gallon and 55 gallon

Cautions

Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

Pro-Seal R.O.C. Hard™



16541 Redmond Way • Suite 363C • Redmond, WA 98052
Phone: 800.349.7325 • information@prosealproducts.com
www.prosealproducts.com • © Copyright Pro-Seal

Pro-Seal R.O.C. Hard™



Non-Solvent Surface Hardening & Polishing Agent

Specifications

Test	Data	Value
Water absorption	Low air content	.08%
Water absorption	Normal air content	.14%
ASTM C 156 AASHTO M-155	Significant improvement in curing against hairline cracking due to shrinkage	X 100p negative to zero
ASTM C 672	Freeze thaw	No damage
ASTM C 672	Ambient	7%
ASTM C 672	At 2.45 cm chloride content	1.5%
ASTM C 672	At 2.45 cm Non air entrained	1.8%
ASTM C 672	At 2.45 cm Air entrained	7%
Brookfield viscometer	Viscosity	> 5,000 cps
ASTM 2369-92	V.O.C. content	None

* Data based on laboratory tested materials.

Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

Pro-Seal R.O.C. Hard™



16541 Redmond Way • Suite 363C • Redmond, WA 98052
Phone: 800.349.7325 • information@prosealproducts.com
www.prosealproducts.com • © Copyright Pro-Seal